

TECHNICAL DATA SHEET

PRODUCT IDENTIFICATION : OTOKAP EMBOSS VIRGIN

TECHNICAL PROPERTIES

SPECIFICATION	STANDART	PRODUCT
Total thickness	EN ISO 24346	1.20 mm (min:-0.10mm max: 0.13mm)
Total weight	EN ISO 23997	1600 gr/m2 (max:+%13 min: -%10)
Wear layer thickness	EN ISO 24340	0.10mm (max:+%13 min: -%10)
Roll width	EN ISO 24341	200 cm
Roll length	EN ISO 24341	25 min
PERFORMANCE		
Wear Layer Group	EN 660-2	GROUP T
Binder content	ISO 10582	TYPE 1
Residual Indentation	EN ISO 24343-1	≤0.1 mm
Dimentional stability after Exposure heat	EN ISO 23999	≤0.4 %
Curling after Exposure heat	EN ISO 23999	Max:8mm
Flexibility	EN ISO 24344	No Crack
Hardness	ISO 7619	85±5 ShA
Back Layer		TX100X